

High Pressure Fiberglass Line Pipe Product Guide

For Oil & Gas Applications

High Pressure Line Pipe Product Summary Table

			S. T. A. M. P					Pressure Range By Diameter (Min./Max.)										Joint Types Available		
Brand Name	Epoxy Curing Agent	Design Basis	Size Range (in.)	Max. Operating Temperature (°F)	Applications	Media	Pressure Range (psi.)	1½	2	2½	3	4	5	6	8	10	12			
Star	Anhydride	Standard	1-1/2 - 8	150	P, I, T, D	O, W, G, C ¹ , H ¹	500 - 3000	1750 3000	1250 3000	1000 3000	800 2900	500 3000	500 2000	500 2000	500 1750			ACT	PGT	Flange
Star	Anhydride	API 15HR	1-1/2 - 8	150	P, I, T, D	O, W, G, C ¹ , H ¹	500 - 2500	1250 2500	1000 2500	750 2500	500 2500	500 2500	500 1750	500 2000	500 1500			ACT	PGT	Flange
Star	Anhydride	Standard	8 - 12	150	P, I, T, D	O, W, G, C ¹ , H ¹	1000 - 3000								1000 3000	1000 2500	1000 2250	SSS-HP		Flange
Star	Anhydride	API 15HR	8 - 12	150	P, I, T, D	O, W, G, C ¹ , H ¹	1000 - 2500								1000 2500	1000 2250	1000 2000	SSS-HP		Flange
Centron	Anhydride	Standard	2 - 4	150	P, T, D	O, W, C ¹ , H ¹	500 - 800		500 800		500 800	500 800						CEN		Flange
Centron	Anhydride	Standard	1-1/2 - 6	150	P, I, T, D	O, W, G, C ¹ , H ¹	500 - 3500	1250 3500	1000 3500	800 3000	800 3000	500 1500	500 1500	500 1000				SP		Flange
Centron	Anhydride	API 15HR	1-1/2 - 6	150	P, I, T, D	O, W, G, C ¹ , H ¹	500 - 2000	1000 2000	1000 2000	1000 2000	750 2000	750 1250	750 1250	500 750				SP		Flange
Centron	Anhydride	Standard	4 - 10	150	P, I, T, D	O, W, G, C ¹ , H ¹	400 - 2500					800 2500		800 2500	800 ⁶ 1750	500 ⁸ 2000	500 ¹⁰ 800	SPH	SPH-HP	Flange
Centron	Anhydride	API 15HR	4 - 10	150	P, I, T, D	O, W, G, C ¹ , H ¹	500 - 2000					750 2000		500 2000	500 ⁶ 1750	500 ⁸ 1750	500 ¹⁰ 750	SPH	SHP-HP	Flange
Star	Aliphatic Amine	Standard	1-1/2 - 8	200	P, I, T, D	O, W, G, C ² , H	500 - 3500	1500 3500	800 3500	800 3500	500 3500	500 3500	500 2000	500 2500	500 2000			ACT		Flange
Star	Aliphatic Amine	API 15HR	1-1/2 - 8	200	P, I, T, D	O, W, G, C ² , H	500 - 3000	1500 3000	750 3000	750 3000	500 3000	500 3000	750 1000	500 2000	500 1750			ACT		Flange
Star	Aliphatic Amine	Standard	8 - 12	200	P, I, T, D	O, W, G, C ² , H	500 - 1250								500 1250	500 1250	500 1250	SSS		Flange
Centron	Aromatic Amine	Standard	2 - 4	212	P, T, D	O, W, C, H	500 - 800		500 800		500 800	500 800						CEN		Flange
Centron	Aromatic Amine	Standard	1-1/2 - 6	212	P, I, T, D	O, W, G, C, H	500 - 3500	1250 3500	1000 3500	800 3000	800 3000	500 1500	500 1500	500 1000				SP		Flange
Centron	Aromatic Amine	API 15HR	1-1/2 - 6	212	P, I, T, D	O, W, G, C, H	500 - 2000	1000 2000	750 2000	750 2000	500 2000	500 1250	500 1250	500 750				SP		Flange
Centron	Aromatic Amine	Standard	4 - 10	212	P, I, T, D	O, W, G, C, H	400 - 2500					800 2500		800 2500	500 ⁶ 1800	500 ⁸ 2000	400 ¹⁰ 800	SPH	SPH-HP	Flange
Centron	Aromatic Amine	API 15HR	4 - 10	212	P, I, T, D	O, W, G, C, H	500 - 2000					750 2000		500 2000	500 ⁶ 1500	500 ⁸ 1750	500 ¹⁰ 750	SPH	SPH-HP	Flange
Star	Aromatic Amine	API 15HR	1-1/2 - 8	212	P, I, T, D	O, W, G, C, H	500 - 2500	1750 2500	1000 2500	750 2500	750 2500	750 2000	750 1500	500 1750	500 1250			ACT	PGT	Flange
Star	Aromatic Amine	API 15HR	8 - 12	212	P, I, T, D	O, W, G, C, H	1000 - 2000								1000 2000	1000 1500	1000 1250	SSS-HP		Flange
Fiberspar (E)	Anhydride	API 15HR, 15S (RP)	2 - 6-1/2	140	P, I, T, D, R	O, W, G, C, H	500 - 3500		1100 3500	1100 3500	750 3500	1100 ³ 2750	750 ⁴ 2750	500 ⁵ 2250	500 ⁷ 1500	500 ⁹ 1500		8rd, NPT	Weld, Other	Flange
Fiberspar (X)	Anhydride	API 15HR, 15S (RP)	2 - 6-1/2	180	P, I, T, D, R	O, W, G, C, H	470 - 3300		1100 3300	1100 3300	700 3300	1100 ³ 2600	700 ⁴ 2600	470 ⁵ 2250	470 ⁷ 1400	470 ⁹ 1400		8rd, NPT	Weld, Other	Flange
Fiberspar (XT)	Anhydride	API 15HR, 15S (RP)	2 - 6-1/2	203	P, I, T, D, R	W	425 - 3100		975 3100	975 3100	650 3100	975 ³ 2425	650 ⁴ 2425	425 ⁵ 2000	425 ⁷ 1325	425 ⁹ 1325		8rd, NPT	Weld, Other	Flange

Notes:

Applications: **P** - Production Flow Lines; **I** - Injection Lines; **T** - Transfer Lines; **D** - Disposal Lines; **R** - Rehabilitation of Corroded Lines

Media: **O** - Oil; **W** - Water (Produced, Salt, Fresh); **G** - Natural Gas; **C** - CO₂ or Fluids Containing CO₂; **H** - Sour Services (Fluids Containing H₂S);

C¹ - Temperature Limited to 125°F; **C²** - Temperature Limited to 185°F; **H¹** - H₂S Concentration Limited to 3%

Notes on Diameters: ³ Dia. = 3 1/2; ⁴ Dia. = 4; ⁵ Dia. = 5; ⁶ Dia. = 7 3/4; ⁷ Dia. = 6; ⁸ Dia. = 8; ⁹ Dia. = 6 1/2; ¹⁰ Dia. = 10

(RP) indicates Recommended Practice

Product Series

Star Anhydride - ACT or PGT

- Thread design per API Specification 5B
- Full line of filament wound fittings
- Standard or API design

Applications: Suitable for all, sweet or mildly sour, oil field services with limited CO₂ content

Features: Minimum 20 year service life at full rating based on 150°F design temperature and nominal (standard) or minimum (API) wall thickness

Star Anhydride - SSS-HP

- 2 thread-per-inch mechanical joint with O-ring seal
- Filament wound elbows, couplings, and flanges available
- Standard or API design

Applications: Designed for transfer of high volumes of fluid at high pressure. Fast assembly joint.

Features: Full pressure rating up to 150°F

Centron Anhydride - CEN

- 4 thread-per-inch modified ACME thread with O-ring seal
- Full line of filament wound fittings
- Standard or API design

Applications: Low pressure, fast-assembly, flowline product for general service piping needs; larger than normal ID

Features: Not intended for gas service. Sulfur-cured O-ring not recommended for sour service

Centron Anhydride - SP, SPH, SPH-HP

- 4 thread-per-inch round form (SP) or buttress (SPH) sealing thread secondary O-ring seal
- Full line of filament wound fittings

Applications: Proprietary joint designs for fast, reliable assembly

Features: Position-based thread assembly. Suitable for gas service

Star Aliphatic Amine - ACT

- Similar to Anhydride cured offering, with higher performance characteristics with regards to temperature and resistance to CO₂ and H₂S exposures
- Standard or API design

Applications: Designed for fast, reliable assembly

Features: Position-based thread assembly. Suitable for gas service

Star Aliphatic Amine - SSS

- 2 thread-per-inch mechanical joint with O-ring seal
- Full line of filament wound fittings
- Standard design only

Applications: Designed for high volume lines at high temperatures; fast assembly joint well suited for long lines

Features: Standard size O-ring used. A variety of elastomer materials are available

Centron Aromatic Amine - CEN

- 4 thread-per-inch modified ACME thread with O-ring seal
- Higher temperature rated version of Anhydride cured product with higher performance in CO₂ and H₂S environments

Applications: Provided for transfer of high temperature, more corrosive fluid handling lines

Features: Temperature performance of O-ring material should be considered during selection

Centron Aromatic Amine - SP, SPH, SPH-HP

- 4 thread-per-inch round form (SP) or buttress (SPH) sealing thread with secondary O-ring seal
- Standard or API design

Applications: Combines characteristics of double-seal joint, high pressure and high temperature designs

Features: Highly regarded product for wide variety of upper-end services up to 212°F

Star Aromatic Amine - ACT, PGT

- Premium product available with ACT and PGT joint
- Full line of filament wound fittings
- API design only

Applications: Product of choice for severe service, regulated systems

Features: Premium product line providing highest allowable operating temperature

Star Aromatic Amine - SSS-HP

- 2 thread-per-inch mechanical joint with O-ring seal
- Extended range product at upper end of available design and performance
- API design only

Applications: Provide high flow capacity for hot, corrosive fluids in characteristically large systems

Features: Product line expands the range of services covered by fiberglass pipe

Fiberspar (E), (X) and (XT)

- High performance, only true Glass Reinforced Epoxy (GRE) spoolable line pipe product
- Designed with various grades of thermoplastics in bonded liner and formed jacket layers, enveloping the GRE structural wall
- Connectors employ positive grip on GRE layer and are designed to be reusable and are immune to viscoelastic creep which plagues other designs

Applications: Product is rapidly deployed and is installed by Certified Installers thoroughly trained and tested by Fiber Glass Systems personnel

Features: This is not thermoplastic pipe made stronger, it is GRE pipe made spoolable

Standard Design and API Design

Long-term regression testing is done on a set of identical samples with pressure held steady at predetermined stress levels to cause short-term, medium-term and long-term failures, according to ASTM D2992 - Procedure B. Statistical analysis of the time vs. stress data points is performed and plotted on log/log scales, including least-squares fit of the regression line, extrapolation to the design life, calculation of variance to qualify the consistency of the data and upper and lower confidence limits. Standard design utilizes a Long Term Hydrostatic Strength (LTHS) at 100,000 hours (11.4 years) or 175,200 hours (20 years) and applies a 0.5 or 0.67 Service Factor to determine the Hydrostatic Design Stress (HDS), which is then applied to the nominal wall thickness of the pipe to determine its pressure rating. API design uses a 0.67 Service Factor at a 20-year design life, utilizing the 95% Lower Confidence Limit (LCL), and applies it to the minimum wall thickness. For a detailed explanation, please contact Fiber Glass Systems Application Engineering. Standard design product is 100% factory hydro tested at 1.25 times its rated pressure. API design product is 100% factory hydro tested at 1.50 times its rated pressure.

Connections


ACT

Molded, 8 threads per inch using a graphite, ceramic and epoxy composite for high performance applications. Threads conform to API Standard 5B (14th Edition).




SSS, SSS-HP

“STAR Super Seal” heavy-duty, modified ACME (non-sealing), 2 thread per inch threads with an o-ring seal.



PGT

Ground threads produced with diamond-coated, profiled grinding wheels and numerical controlled grinding equipment. API conformance as described for ACT.



CEN

Centron CEN is similar to the SSS with 4 threads per inch.

Flange

ANSI 16.5 compliant flange connection for full range of pressure ratings. Flanges for STAR and Centron products have internal female threads and assemble on to male threaded pipe ends or threaded pipe nipples. Fiberspar flanged Service End Connectors are metallic and are welded to body of the connectors.

SP

Ground, round-form, 4 threads per inch threads providing a position-based seal, complemented with an o-ring seal.




SPH, SPH-HP

Ground, trapezoidal-form (buttress), 4 threads per inch threads providing a high strength, position-based seal, complemented with an o-ring seal.

NPT Threads or Weld-Ends

Unique to Fiberspar within Fiber Glass Systems, pipe to pipe connectors are used when connecting pieces of spoolable pipe together, whether for extending the length of the line or for repairing a damaged section.



Note: All female fiberglass threads are made on profile tooling to form mating threads to the male threads as described above.



National Oilwell Varco has produced this brochure for general information only, and it is not intended for design purposes. Although every effort has been made to maintain the accuracy and reliability of its contents, National Oilwell Varco in no way assumes responsibility for liability for any loss, damage or injury resulting from the use of information and data herein. All applications for the material described are at the user's risk and are the user's responsibility. All brands listed are trademarks of National Oilwell Varco.

Fiber Glass Systems

17115 San Pedro Ave., Suite 200
San Antonio, Texas 78232 USA
Phone: 210 477 7500
Fax: 210 477 7560

© 2014 National Oilwell Varco All Rights Reserved
OG1015ENG January 2015